Specification for Lithium-ion Rechargeable Cell

Cell Type : LPT36130290-100PF

Approved	Checked	Prepared
HX Shi	ZH Hu	ZB Zheng

Contents

- 1. Preface
- 2. Description
- 3. Cell Size
- 4. Construction
- 5. Specification
- 6. Test Conditions
- 6.1 Standard Test Conditions
- 6.2 Standard Charge Method
- 7. Electrical Characteristics
- 8. Environmental Characteristics
- 9. Safety Test
- 10. Shipment
- 11. Warranty
- 12. Precautions and Safety Instructions
- 12.1 Standard cell Precautions
- 12.2 Cell Operation Instructions
- 12.2.1 Charging
- 12.2.2 Discharging
- 12.2.3 Storage Recommendation

1. Preface

This Product Specification describes the technique requirements, test procedures and precaution notes of Lithium-ion Rechargeable cell.

2. Description

- 2.1 Product: Lithium-ion Rechargeable cell
- 2.2 Model (Type): LPT36130290-100PF

2.3 Designation:

- 36 130 290- 100 P F
- 1 2 3 4 5 6
- ①: Indicates the Thickness of cell T
 - T 36=36mm, ±1mm
- ②: Indicates the overall Width of cell W
 - W 130=130mm, ±1mm
- ③: Typical battery height H
 - H 290=290mm, ±2mm
- (4): 60 Indicates the capacity of cell

100Ah

⑤: Indicates the performance of cell 代表电池性能

The letter "P" defines high power cell

图 A


6: The letter "F" defines LiFePO4 series cathode

3.Cell Size

For details, please refer to Figure A. Remark: contain package (PVC heat-shrinkable).

4.construction

A cell is made of cathode, anode, separator, aluminum shell and caps.



5.Specification

	Item	Specification	Remark	
5.0 Typical Ca	pacity	102Ah	Temperature:23±2°C 0.3C discharge capacity	
5.1 Minimum (Capacity	100Ah		
5.2 Internal Im	pedance	≤0.5mΩ	By AC 1 KHZ	
5.3 Nominal V	oltage	3.2V		
5.4 Cell Weigh	nt	≤3kg	contain package	
5.5 End-of-cha	arge Voltage	3.65V	At CC mode	
5.6End-of-disc	charge Voltage	2.2V		
5.7Charge Method		0.5C CC/CV		
5.8 Max Pulse Discharge current		500A	Pulse Current width: 5C Under 5 Seconds	
5.9 Max Continuous Discharge current		200A	Continuous Discharge current: Under 2C	
5.10 Max Pulse charge current		100A	Pulse Current width:2c Under 10Seconds	
5.11 Standard	charge current	50A	0.5C	
5.12Cycle Life		≥2500 cycles	50A Continual Charge&Discharge (100% DOD) Rest Capacity over80%	
5.13 Operating Temperature	Charging Temperature	0∼50°C	Recommended temperature range for long term storage is $0 \sim +50^{\circ}$ C	
Range	Discharging		Recommended temperature range	
	Temperature	-20∼50°C	for long term storage is -20 \sim +50°C	
	Storage Temperature	-10∼45℃	Recommended temperature range for long term storage is -10 ~ +45°C	
5.14 Shelf Life	,	3year	Typical value from ship state	

5.15 Appearance	Without break, scratch, distortion, contamination, leakage
	and so on

6.Test Conditions

6.1 Unless otherwise specified, all tests stated in this Product Specification are conducted at temperature

23°C±2°C and Humidity<75%RH.

6.2 Standard Charge Method

The "Standard Charge" means in an ambient temperature of 23°C±2°C, charging the Cell at a constant

current of 0.5C until the voltage is 3.65V, then charged at a constant voltage of 3.65V Until current is less than 0.05C.

7. Electrical characteristics

7. Electrical	ectrical characteristics		
Test Item	Test Method	Criteria	
7.1 High Temperature Performance	A cell is charged in accordance with 6.2,and stored in an ambient temperature of $50^{\circ}C\pm 2^{\circ}C$ for 4hrs,then discharged to cut-off voltage at a constant current of 0.5C. After that, fetch out the cell and place it in the ambient temperature of $23^{\circ}C\pm 2^{\circ}C$ for 4hrs, then check its appearance.	 Capacity retention:≥90%; No distortion, no rupture. 	
7.2 Low Temperature Performance	A cell is charged in accordance with 6.2,and stored in an ambient temperature of $-20^{\circ}C\pm2^{\circ}C$ for 20hrs,then discharged to cut-off voltage :2.0V at a constant current of 0.5C. After that, fetch out the cell and place it in the ambient temperature of $23^{\circ}C\pm2^{\circ}C$ for 4hrs, then check its appearance.	 Discharge Capacity Percentage Ratio :≥65%; No distortion , no rupture 	
7.3 Room Temperature Powerful Discharge Performance	A cell is charged in accordance with 6.2,and stored in an ambient temperature of $23^{\circ}C\pm 2^{\circ}C$ for 20hrs,then discharged to cut-off voltage :2.2V at a constant current of 3C . After that, fetch out the cell and place it in the ambient temperature of $23^{\circ}C\pm 2^{\circ}C$ for 4hrs, then check its appearance.	 Discharge Capacity Percentage Ratio :≥95%; No distortion, no rupture 	
7.4 Cycle Life (23℃±2℃)	A cell is charged to end-of-charge voltage at a current of 0.5C, and then charged at a constant voltage of 3.65V until the charge current is less than 0.05C,after that stored for 30min; Discharged to cut-off voltage at a constant current of 0.5C,after that, stored 30min prior to next charge- discharge cycle.The cell shall be continuously charged and discharged for 2500 times.	capacity retention:≥80%	

8. Environmental Characteristics

Test Item	Test Method	Criteria
8.1 Constant Temperature and Humidity	A cell is charged in accordance with 6.2,and stored in an ambient temperature of 40 ± 2 °C($90\sim95$ %RH) for 48hrs,then placed in room temperature for 2hrs. After that, check its appearance prior to being discharged to cut-off voltage at a constant current of 0.5C.	1.No distortion ,no, rust no fume, no explosion;2.Capacity retention:≥80%
8.2 Temperature Test	A cell is charged in accordance with 6.2, then heated the cell to be in a oven. then the temperature of the oven is to be raised to the temperature of 70 °C \pm 3 °C and remain for4h at that temperature, then the temperature of the oven is to be dropped to the temperature of 20 °C \pm 3 °C and remain for 4h at that temperature, then the temperature of the oven is to be dropped to the temperature of -40 °C \pm 3 °C and remain for 4h at that temperature, then the temperature of the oven is to be dropped to the temperature of -40 °C \pm 3 °C and remain for 4hrs at that temperature, repeat this for another 9 cycles, after that put the cell in room temperature for at least 24hrs, then check cell's appearance.	No leakage, no fire, no explosion, no vent
8.3 Low-pressur e Test	A cell is charged in accordance with 6.2, then stored it for 6hrs at a vacuum of -0.90mPa, after that put the cell in room temperature for 6hrs, then check cell's appearance.	No leakage, no fire, no explosion, no vent
8.4 Vibration Test	A cell is charged in accordance with 6.2,then installed onto the vibration desk with clamps. Equipment parameters of frequency and amplitude are as follows(the frequency is to be varied at the rate of 1oct/min between 10 and 55 Hz, and repeat vibration for 30min.The cell is to be tested in three mutually perpendicular directions): frequency:10Hz~30Hz amplitude: 0.38mm frequency:30Hz~55Hz amplitude: 0.19mm	1.No scratch, no fire, no explosion, no vent;2.The voltage is not less than3.35V.

9. Safety Test

All below tests are carried out on the equipment with forced ventilation and explosion-proof device. Before test, all cells are charged in accordance with 6.2, and stored 24hrs prior to testing.

Test Item	Test Method	Criteria
9.1 55℃ Short- circuit Test	A oven is to be raised to the temperature of 55°Cand remain for 10min at that temperature. A cell is to be placed into the oven and remain for 30min~40min.Then the Cell is to be short-circuited by connecting the positive and negative terminals of the cell with copper wire having a maximum resistance load of 50m Ω .Monitor its temperature while testing, the cell is to be discharged until the cell case temperature has returned to be 10°Cless then peak temperature.	1.No fire, no explosion 2.Max.temp.< 150℃
9.2 Overcharge Test (3C/5V)	A cell is discharged to cut-off voltage at CC of 0.5C.then it is to be subjected to CC/CV power by connecting its positive & negative terminal, then set the current as 3C,the voltage as 5V,after that, Charge the cell up to 5V at CC of 3C ,until that last 7h at the voltage of 5V or the voltage is no more increased.	No fire, no explosion
9.3Forced-Dis charge Test	A cell is discharged to cut-off voltage 0V at a constant current of 1C.	No fire, no explosion,
9.4 Crush Test	A cell is to be placed on the crush flat, the axis is parallel to the crush flat ,it is to be crushed between two flat surfaces. Crushing force is approximately 13 KN and hold for 1 min.	No fire, no explosion
9.5 Impact Test	A cell is to be placed on the impact flat.A Φ 15.8mm bar is to be placed on the center of the cell.A 9.1kg weight is to be dropped from a height of 610mm onto the cell, the distortion is allowed.	No fire, no explosion
9.6 Heating Test (130℃)	A cell is to be heated in a circulating air oven. The temperature of the oven is to be raised at a rate of $5^{\circ}C\pm2^{\circ}C$ per minute to a temperature of $130^{\circ}C\pm2^{\circ}C$ and remain for 30min at that temperature before the test is discontinued.	No fire, no explosion

10.Shipment

The Cell shall be shipped in voltage range of $3.2 \sim 3.4$ V or in accordance with customers' requirement. The remaining capacity before charging shall be changed depending on the storage time and conditions.

11.Warranty

The Warranty period of cell is made according to business contract, However, even though the problem occurs within this period, LPT won't replace a new cell for free as long as the problem is not due to the failure of LPT manufacturing process or is due to customer's abuse or misuse.

LPT will not be responsible for trouble occurred by handling outside of the precautions in instructions.

LPT will not be responsible for trouble occurred by matching electric circuit, cell pack and charger.

LPT will be exempt from warrant any defect cells during assembling after acceptance.

12.Precautions and Safety Instructions

Lithium-ion rechargeable batteries subject to abusive conditions can cause damage to the cell and/or personal injury. Please read and observe the standard cell precautions below before using utilization.

Note 1. The customer is required to contact LPT in advance, if and when the customer needs other applications or operating conditions than those described in this document.

Note 2. LPT will take no responsibility for any accident when the cell is used under other conditions than those described in this Document.

12.1 Standard cell Precautions

- a. Do not expose the cell to extreme heat or flame.
- b. Do not short circuit, over-charge or over-discharge the cell.
- c. Do not subject the cell to strong mechanical shocks.
- d. Do not immerse the cell in water or sea water, or get it wet..
- f. Do not disassemble or modify the cell.
- g. Do not handle or store with metallic like necklaces, coins or hairpins, etc.
- h. Do not use the cell with conspicuous damage or deformation.
- i. Do not connect cell to the plug socket or car-cigarette-plug.
- j. Do not make the direct soldering onto a cell.
- k. Do not touch a leaked cell directly.
- I. Do not use for other equipment.
- m. Do not use Lithium-ion cell in mixture.
- n. Do not use or leave the cell under the blazing sun (or in heated car by sunshine).
- o. Keep cell away from children.
- p. Do not drive a nail into the cell, strike it by hammer or tread it.
- q. Do not give cell impact or fling it.
- 12.2 Cell Operation Instructions
- 12.2 Cell Operation Instructions
- 12.2 Cell Operation Instructions
- 12.2.1 Charging
- a. Charge the cell in a temperature range of 0°C to +50°C.

b. Charge the cell at a constant current of 0.5C until 3.65V, and then at a constant voltage of 3.65V until0.05C.

Charge rates greater than 1C are NOT recommended. (C : Rated Capacity of cell)

12.2.2 Discharging

a. Recommended cut-off voltage to 2.2V. Recommended max continuous discharge current is 2C $_{\circ}$

b. For maximum performance, discharge the cell in a temperature range of -20°C to +50°C.

12.2.3 Storage Recommendations

In case of long period storage (more than 3 months), storage the cell at temperature range of $-10 \sim +45^{\circ}$ C, low humidity, no corrosive gas atmosphere. No press on the cell! And more than 3 months need to put a charge according to the standard charge and discharge process